

HeliBond

High performance,
injectable, cementitious,
non-shrink grout


Applications

- For bonding metal components into masonry type substrates
- Used to bond HeliBars into masonry for crack stitching, lintel repair and creation, masonry beaming and CemTie installation




Features


- Non-shrink, non-gassing, thixotropic grout
- Flows easily under pressure to fill voids
- Rapidly develops compressive strength
- Cures to 45N/mm²
- Ready-to-mix components supplied in two-pack sets to reduce waste



Repairing brick arch lintels



Creating masonry beams



Crack stitching



Over 100 standard repair specifications are available online, covering all common structural faults.

For full Product Information, Case Studies and downloadable Repair Details go to:
www.helifix.co.uk/products/grouts-resins/helibond-grout



Directions for use



1. Empty the contents of the liquid pack into the pail



2. Add the contents of the powder pack



3. Stir thoroughly using a power-driven paddle mixer. Do not attempt to mix by hand as this is likely to lead to erratic results



4. Check the piston is a snug fit in the cartridge and adjust in accordance with the pointing gun instructions. Load the mixture into the cartridge in the pointing gun immediately after agitating



5. Inject into the slot or hole in a continuous operation. Typical working life of the mixture in the pail is around 2 hours **with re-agitation**. The cartridge should be emptied within 5 minutes. If the injection process is interrupted for any reason, empty any cartridge contents back into the bucket and re-stir until it again reaches a smooth injectable consistency

Note

- If the pail is to be re-used ensure that it is completely clean before loading fresh material
- Pointing may be carried out as soon as the HeliBond has started to set
- After use, clean all tools, mixers and containers with clean, fresh water

In general, a minimum clearance of 2mm all around the component will be adequate but should be increased to overcome drill wander in deeper holes, 500mm+, or to accommodate highly absorbent substrates. For Helifix bars and ties the following will generally apply.

Performance data

Compressive strength: (at 20°C)	2 days – 15N/mm ² 7 days – 25N/mm ² 28 days – 45N/mm ²
Pot life:	2 hours at 20°C
Storage conditions:	Cool, dry, frost-free conditions away from direct sunlight
Storage temperature:	5°C to 25°C
Pail storage:	Pails to be stacked no more than four high
Shelf life:	12 months under normal conditions
Pack size:	3.0 litres
RECOMMENDED TOOLING	
For mixing components:	Power drill and paddle mixer
For injection into slots:	Helifix Pointing Gun Kit - CS
For injection into holes:	Helifix Pointing Gun kit - HD
Also available with pneumatic power	

Part diameter	Slot width	Hole diameter
6mm	10mm	10-12mm
8mm	12mm	14-18mm
10mm	14mm	16-18mm

Health and safety

HeliBond contains Portland Cement and is therefore alkaline when wet. Unnecessary skin contact should be avoided. In case of eye contact, the eye must be irrigated with gently running clean, fresh water and medical attention sought.

A separate Health & Safety Data sheet is available on request.